

### RTV 200 Series Flowable Sealants

Part No	Viscosity ,cPs	Hardness	Tensile Strength, psi	Elongation, %	Skin Over Time, minutes	Colour
200-102	70,000-110,000	A25	200	250	30	Black
200-107	70,000-110,000	A25	200	250	30	White
200-202	20,000-35,000	A15	50-100	245-300	20	Black
200-250	21,000-40,000	A15			60	Translucent
200-251	8,000-12,000	A20	30-50	80-120	20	Translucent
200-257	20,000-35,000	A15	50-100	245-300	20	Translucent
200-260	300-800	A20	30-50	80-120	60	Clear

