

RTV 400 Series Low Adhesion Sealants

Part No	Viscosity ,cPs	Hardness	Tensile Strength, psi	Elongation, %	Skin Over Time, minutes	Colour
400-900	320,000-550,000	A40	200-250	250-350	30-40	White
400-950	150,000-250,000	A35	200-250	250-350	30-40	Translucent

