

RTV 800 Series UV Curable Sealants

Part No	Viscosity ,cPs	Shore Hardness	Tensile Strength, psi	Elongation, %	Skin Over Time, minutes	Colour	Specification/ Rating
800-230	20,000-35,000	A25	50	500		Hazy	
800-235	90,000-125,000	A15	150	425		Hazy	
800-240	85,000-135,000	A15	150	425		Hazy	
800-245	4,000-6,000	A10-15	100	300		Hazy	
800-255	1,000-2,000	A15	50	25	60	Hazy	
800-260	2,000-5,000	A15	100	100	60	Clear	UL746E
800-270	2,000-5,000	A20	50	25	60	Clear	
800-400	Paste	A30	450	1400		Translucent	
800-610	<750	80 Shore 00				Clear	
800-620	20,000-25,000	60 Shore 00				Clear	

