

Versilube General Purpose/Dielectric Compounds

Part No	Appearance	Penetration (Worked 60X)	Bleed	Evaporation	Dissipation Factor	Water Washout	Volume Resistivity Ω .cm
G623	Translucent paste	200-300	5% max	3% max	0.0002		
G624	Translucent paste	200-310	8% max	2% max	-0.0010	0.86%	1.1×10^{15}
G627	Translucent paste	200-300	1% max	3% max	-0.0001		1.0×10^{15}
G635	Translucent paste	200-300	10% max	3% max	0.0019	0.4%	4.8×10^{14}
G661	Translucent paste	200-300	1% max	2% max	0.0016	1.3%	4.0×10^{14}
G662	Translucent paste	200-300	1% max	2% max	0.0016	<1.0%	4.0×10^{14}
G687	Translucent paste	200-300	10% max	3% max	-0.0005	3%	5.5×10^{14}
G697	Cream to tan paste	260-320	4% max	2% max			

