

Versilube Silicone Greases

Part No	Appearance	Penetration (Worked 60X)	Bleed	Evaporation	Dropping Point	Water Washout	Corrosion (Copper Substrates)
G321	Off white / Tan paste	260-300	4% max	3% max	190°C min	3%	No effect
G322L	Yellow paste	270-330	15% max	3% max	190°C min	3%	No effect
G326	Tan paste	290-320	15% max	3% max	190°C min	3%	No effect
G330M	Off white / Tan paste	250-300	8% max	3% max	190°C min	4%	No effect
G351	Off white / Tan paste	260-300	12% max	2% max	190°C min	20%	No effect