

Versilube Thermally Conductive Compounds

Part No	Appearance	Penetration (Worked 60X)	Bleed	Evaporation	Dissipation Factor	Volume Resistivity Ω .cm	Thermal Conductivity
G641	White paste	240-320	1% max	2% max	0.0074	1.2×10^{15}	0.7W/mK
G644	White paste	290-330	2% max	2% max	0.0032	1.5×10^{15}	0.38BTU/ft ² -°F-hr