

RTV 600 Series Addition Cure Sealants

Part No	Viscosity ,cPs	Hardness	Tensile Strength, psi	Elongation, %	Skin Over Time, minutes	Colour
600-160	5,000-10,000	A70-80	125	200	<15	Grey
600-170	2,000-5,000	A30-50	125	200	<15	Dark Grey
600-180	5,000-9,000	A50-60	1100	240	<20	Clear
600-200	4,000-8,000				10-15	Clear